

# Parquet lacquer UA



1L

## PRODUCT DISCRIPTION

Parquet Lacquer UA is a one component solvent based polyurethane lacquer. Parquet Lacquer UA is designed to protect heavy used wooden floors such as commercial spaces. A hardener can be added to increase the chemical and mechanical resistance.

## TECHNICAL DATA

DILUTION	WHITE SPIRIT
SOLID CONTENT	+/- 52% IN WEIGHT
VISCOSITY	+/- 150-200 SEC - DIN 4
GLOSS	MAT, SATIN AND GLOSSY

## PREPARATION

The surface must be clean. If necessary, sand and degrease the wood.



## USER INSTRUCTIONS

Apply the Lacquer with a brush or roller. It's recommended to apply 3 coats. Intermediate sanding between coats with grain 180. In order to obtain better results, a hardener can be added to the varnish (5%). Mix the hardener with the varnish and let rest for 15 minutes. After mixing with the hardener, the pot life is +/- 4 hours. Afterwards the product is unusable.



## DRYING TIMES

Dust-free after +/- 1 hour  
Recoatable after +/- 8 hours  
Slightly chargeable after 24 hours.

The drying times are highly dependent on the applied quantity, the environmental temperature, the humidity and ventilation.

## APPLYING QUANTITY

8 - 10 m<sup>2</sup>/per liter per coat.

## AFTER TREATMENT

Use Hard floor fresh Ciranova for regular maintenance. For periodic maintenance use Hard Floor polish Ciranova. For deep cleaning of a varnished floor and to remove old polish layers, use Hard Floor Cleaner.

## PRODUCT INFORMATION

Storage: 1 year in original and well closed packaging.

Ciranova<sup>®</sup> products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However, they are drawn to our best knowledge and ability. The user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.

## PRODUCED BY DEBAL COATINGS NV

Industrieweg 29 – B 8800 Beveren-Roeselare  
tel +32 (0) 51 30 11 40 fax +32 (0) 51 31 26 48  
www.ciranova.be ciranova@ciranova.be