

CIRANOVA[®]
SINCE 1929



5L

1L

Ciranova[®] products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However, they are drawn to our best knowledge and ability. The user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.

PRODUCED BY DEBAL COATINGS NV

Industrieweg 29 – B 8800 Beveren-Roeselare
tel +32 (0) 51 30 11 40 fax +32 (0) 51 31 26 48
www.ciranova.be ciranova@ciranova.be

TECHNICAL DATA SHEET

YACHT VARNISH

PRODUCT DISCRPTION

Ciranova Yacht varnish is designed to protect wood that is exposed to extreme weather events such as the deck of boats, wainscoting, wood exposed to the maritime climate, etc. The Yacht varnish has a high gloss and can also be applied on indoor wood.

TECHNICAL DATA

BRILLIANCE DEGREE	GLOSSY
DENSITY	0,93
VISCOSITY	100 SEC - DIN 4
SOLID CONTENT	65%
CONFORM THE EUROPEAN DECO-PAINT DIRECTIVE 2010	

PREPARATION

All traces of previous coatings (paint, Varnish, stain) should be removed. If necessary, sand the wood en remove the dust. Try to avoid sharp corners so that all wood is covered nicely by the Yacht Varnish.

USER INSTRUCTIONS

OUTSIDE: apply the Yacht varnish with a brush or roller. Apply 3 to 4 thin layers depending on the kind of wood and exposure to the weather. Please consult the technical service for application with a spray gun. INTERIOR: apply 2 thin coats with brush or roller.



DRYING TIMES

- dust-dry after 1 hour.
- sandable/ chargeable after 24 hours
- Fully hardened after + / - 1 week



APPLYING QUANTITY

10 to 12 m² / liter per layer, depending on the type of wood.

AFTER TREATMENT

Lightly sand the wood that needs to be maintained and remove the sanding dust. Apply 1 or 2 new layers of yacht varnish.

PRODUCT INFORMATION

Durability: 1 year in original packing.

SPECIAL QUALITIES

After use, clean the tools with white spirit.